

LA-UR-17-20887

Approved for public release; distribution is unlimited.

Title: Uranium Conversion & Enrichment

Author(s): Karpus, Peter Joseph

Intended for: Introductory Course on the Nuclear Fuel Cycle for NA-21 Personnel

Issued: 2017-02-06

Disclaimer:

Los Alamos National Laboratory, an affirmative action/equal opportunity employer, is operated by the Los Alamos National Security, LLC for the National Nuclear Security Administration of the U.S. Department of Energy under contract DE-AC52-06NA25396. By approving this article, the publisher recognizes that the U.S. Government retains nonexclusive, royalty-free license to publish or reproduce the published form of this contribution, or to allow others to do so, for U.S. Government purposes. Los Alamos National Laboratory requests that the publisher identify this article as work performed under the auspices of the U.S. Department of Energy. Los Alamos National Laboratory strongly supports academic freedom and a researcher's right to publish; as an institution, however, the Laboratory does not endorse the viewpoint of a publication or guarantee its technical correctness.



Uranium Conversion & Enrichment

Pete Karpus

February 2017

Introduction

- The isotopes of uranium that are found in nature, and hence in 'fresh' Yellowcake', are not in relative proportions that are suitable for power or weapons applications.
- The process of obtaining the proper proportions of these isotopes is called enrichment
- Yellowcake is not in a form that is suitable for enrichment methods so the material must first go through a process called 'conversion'

UNCLASSIFIED


Conversion Introduction

- Enrichment technologies require uranium to be in a gaseous form and not a solid or powder such as U_3O_8 yellowcake
- Uranium Hexafluoride (UF_6) is solid at standard atmospheric pressure but will transform directly to a gas above 134°F (57°C)
 - The direct solid-gas transformation is called 'sublimation'
- The goal of conversion then is to transform the U_3O_8 yellowcake into UF_6


UNCLASSIFIED

Wet Process Conversion Overview

e.g. at **COMURHEX-Malvési** plant in Narbonne, France.




Calcination and Reduction with H₂




UNCLASSIFIED

Hydrofluorination ($\text{UO}_2 \rightarrow \text{UF}_4$)

- Highly corrosive hydrofluoric acid (HF) is used to convert UO_2 to uranium tetrafluoride (UF_4)
 - $\text{UO}_2 + 4\text{HF} \rightarrow \text{UF}_4 + 2\text{H}_2\text{O}$
- The UF_4 slurry is then dried and calcined to remove all water



UF_4 reacts slowly with water to produce HF



<https://www.youtube.com/watch?v=xTFFTQ-bCPI>

UNCLASSIFIED

Fluorination ($\text{UF}_4 \rightarrow \text{UF}_6$)

- HF is dissociated via electric current and forms H_2 and F_2 diatomic molecules
- UF_6 is made by contact of gaseous fluorine with the UF_4 powder in a flame reactor.

The reaction is exothermic and occurs at very high temperatures

Unburned UF_4 collects at the bottom of the reactor and is re-circulated back into the reactor inlet

UF_6 gas is filtered and then chilled and recovered in crystalline form





<http://www.aveva.com/EN/operations-757/conversion-the-fluorination-of-uranium-in-2-stages.html>

UNCLASSIFIED

Properties of UF₆

- Solid UF₆ is a white, dense, crystalline material that resembles rock salt
- UF₆ sublimates at standard atmospheric pressure above 134°F (57°C)
- UF₆ reacts with water to form highly corrosive hydrofluoric acid (HF)



FMA8801

<http://web.evs.anl.gov/uranium/guide/uf6/propertiesuf6/index.cfm>

UNCLASSIFIED

Storage & Transport of UF₆

- Following conversion UF₆ is stored in large robust cylinders
- These cylinders are then transported to enrichment facilities by various means



Type 48Y UF₆ Cylinders


- Used for natural and depleted uranium
- Holds 12,500 kgs of UF₆ (8,450 kgs U)
- A 48Y cylinder filled with natural uranium contains 60.1 kgs of ²³⁵U.
- Nominal wall thickness 16 mm

UNCLASSIFIED

UF6 Cylinder Rupture

EXECUTIVE SUMMARY

On January 4, 1986, at 11:30 a.m., a Model 48Y cylinder filled with uranium hexafluoride (UF_6) ruptured while it was being heated in a steam chest at the Sequoyah Fuels Corporation facility near Gore, Oklahoma. The incident resulted in the death of one plant worker and injuries to several others as a result of exposure to hydrofluoric acid, a reaction product of UF_6 and airborne moisture.



Sequoyah Fuels Corporation Gore, Oklahoma:

1 fatality
37 workers hospitalized
21 locals hospitalized
Shut down 1993

https://en.wikipedia.org/wiki/Sequoyah_Fuels_Corporation

https://en.wikipedia.org/wiki/Uranium_hexafluoride

UNCLASSIFIED

Who does Uranium Conversion?

Company	Nameplate capacity (tonnes U/yr as UF ₆)	Approx capacity utilisation 2015	Capacity utilisation 2015, tU/yr
Cameco, Port Hope, Ont, Canada	12,500	70%	8750
Springfields Fuels, UK	(closed August 2014)	0%	0
TVEL at Siberian Chemical Combine, Seversk, Russia	12,500	100% assumed	12,500
Comurhex (Areva), Malvesi (UF ₄) & Tricastin (UF ₆), France	15,000	70%	10,500
Converdyn, Metropolis, USA	15,000	70%	10,500
CNNC, Lanzhou, China	5000	unknown	4000
IPEN, Brazil	100	70%	70
World Total	60,100		46,320

<http://www.world-nuclear.org/information-library/nuclear-fuel-cycle/conversion-enrichment-and-fabrication/conversion-and-deconversion.aspx>

UNCLASSIFIED

Uranium Enrichment

UNCLASSIFIED

Definition of Uranium Enrichment

- Only three isotopes of uranium are found in nature
 - ^{238}U (99.27%)
 - ^{235}U (0.72%)
 - ^{234}U (0.006%)
- Categories of Enrichment ($E = \% \text{ of } ^{235}\text{U}$)
 - Depleted Uranium (DU) $E < 0.72 \%$
 - Natural Uranium (NU) $E = 0.72 \%$
 - Enriched Uranium $E > 0.72\%$
 - Low Enriched Uranium (LEU) $0.72\% < E < 20.0 \%$
 - High Enriched Uranium (HEU) $E \geq 20.0 \%$

UNCLASSIFIED

Enrichment Methods

■ Gaseous Diffusion

- 1st generation developed in 1940's
- Least efficient
- Huge footprint and energy requirements

■ Gas Centrifuge

- 2nd generation developed in 1940's
- Mid efficiency
- Smaller footprint and energy requirements
 - Centrifuge plants only require ~ 5% energy as gas diffusion facilities

■ Laser Isotope Separation

- 3rd generation developed in the 2000's
- Most efficient
- Potentially smallest footprint and energy requirements

UNCLASSIFIED

Separative Work Units

Separative Work Units (SWUs) represent the effort required to separate ^{235}U from ^{238}U . SWUs are tallied in kilograms or metric tons

To produce 100 kg with 0.3% tails requires ¹ :			
		Approx. Electricity Required (MW-hr)	
Enrichment	kg SWU Required	Gaseous Diffusion	State-of-the-Art Centrifuge
3.0%	342	855	17.1
4.0%	528	1,320	26.4
20.0%	3,832	9,580	191.6
90.0%	19,294	48,235	964.7
3.5 → 20.0%	1,160		
20 → 90.0%	1,848		

¹ Uranium SWU calculator: www.fas.org

UNCLASSIFIED

Online SWU Calculator

<http://www.urengo.com/swu-calculator/>

The URENCO SWU Calculator

SWU stands for Separative Work Unit.

It is the standard measure of the effort required to increase the concentration of the fissionable ^{235}U isotope.

Choose your relevant calculator from the list below. Enter the known quantities before pressing the calculate button to see the result.



Calculate Feed and SWU for 1kgU EUP

Product Assay : % ^{235}U

Tails Assay : % ^{235}U

Feed Assay : % ^{235}U

Calculate

For 1kgU EUP :

Feed Quantity: kgU as UF_6

SWU Quantity: SWU

Note that the independent variables do not include energy or \$\$\$

UNCLASSIFIED

SWUs and the 20 % Level

Separative Work Unit (SWU):

This is a complex unit that represents the effort that is required to enrich uranium.


The bulk of the effort is in taking the enrichment from NU to 20 %!



Natanz Pilot Enrichment Plant

Iran is using IR-1 centrifuges in this facility to produce LEU containing approximately 20% uranium-235. Iran is also testing several types of centrifuges in the facility. Iran's production of LEU enriched to this level has caused concern because such production requires approximately 90% of the effort necessary to produce weapons-grade HEU, which, as noted, contains approximately 90% uranium-235.¹⁴

<http://fpc.state.gov/documents/organization/234999.pdf>



<http://www.world-nuclear.org/info/Nuclear-Fuel-Cycle/Conversion-Enrichment-and-Fabrication/Uranium-Enrichment/>


UNCLASSIFIED

Enrichment Cascade

A single pass through one stage of a gaseous diffusion or centrifuge process is insufficient to achieve practical levels of enrichment.

Therefore, enrichment stages may be connected in both parallel and series in what is called a 'cascade'.


Many cascades may be linked together in a single enrichment facility.



UNCLASSIFIED

Enrichment: Gaseous Diffusion

In the gaseous-diffusion process UF₆ gas is filtered by a semi-porous membrane. The less massive ²³⁵U atoms reach and transit the membrane more easily than ²³⁸U atoms.



UNCLASSIFIED

Gaseous Diffusion

- Used mainly by USA and France
 - Also Russia, China, UK, and Argentina on smaller scales
- E.g. Paducah, Kentucky
 - Produced enriched uranium from 1952 – 2013
 - Covered 740 acres
 - Peak power usage >3000 Megawatts & > 10 million SWU/yr




UNCLASSIFIED


Gas Centrifuge

A gas centrifuge has a spinning rotor within a case. UF_6 gas is fed to the rotor and the more massive ^{238}U atoms drift to the outside leaving the lighter ^{235}U atoms in the center.

Thermal gradients induce convection currents, which further aid in the separation of ^{238}U and ^{235}U .



Gas Centrifuge Performance



Separative Power $\sim \frac{\pi L}{2} \rho D \left(\frac{\Delta M v^2}{2RT} \right)^2 \eta$

L = Rotor length

ρ = Gas density

D = Coeff. of self-diffusion

ΔM = Isotope mass Δ

v = Peripheral rotor velocity

R = Universal gas const.

T = Gas temperature

η = Circulation efficiency

UNCLASSIFIED

Gas Centrifuge Plants

- Operated by :
 - URENCO in UK, the Netherlands, Germany, and USA
 - Areva in France
 - Russia, China, Japan
- Eunice, New Mexico
 - URENCO
 - 3.7 Million SWU/yr*
- Areva is planning to build a 3.3 million SWU centrifuge plant at Eagle Rock in Idaho





*<http://www.world-nuclear-news.org/ENF-Celebrations-at-US-centrifuge-plant-1004147.html>

UNCLASSIFIED

Laser Isotope Separation

In laser-isotope separation, a tunable laser excites and ionizes ^{235}U atoms*. These charged atoms are then collected electrostatically or electromagnetically and separated from the neutral ^{238}U atoms.



* Or molecules in MLIS

UNCLASSIFIED

Laser Isotope Separation

- Even though the interaction is between the laser light and the atomic electrons, it is tuned to ionize based on hyperfine transitions
 - Hyperfine States arise due to interactions between the atomic electrons and the nucleus
 - because the interaction involves the nucleus, the laser can be tuned to a specific isotope and not just an element

UNCLASSIFIED

Laser Isotope Separation

- The SILEX process was developed in Australia by Dr. Michael Goldsworthy and Dr. Horst Struve, working at Silex Systems Limited, a company founded in 1988*
- General Electric (GE) currently has exclusive rights to use the SILEX laser separation process to enrich natural UF₆ gas**
 - SILEX: separation of isotopes by laser excitation
 - On September 25, 2012, NRC staff issued a construction and operating license for the facility.

*https://en.wikipedia.org/wiki/Separation_of_isotopes_by_laser_excitation

**<https://www.nrc.gov/materials/fuel-cycle-fac/laser.html>

UNCLASSIFIED

Tails

- Tails are what remain from the enrichment process
- Depleted Uranium
 - $\sim 0.25 - 0.3\%$ ^{235}U



Depleted UF_6 Cylinder Storage Yard at Portsmouth, OH



Deconversion: chemical removal of the fluorine from UF_6 so that a less-toxic uranium oxide material can be stored as low-level waste

<https://www.nrc.gov/materials/fuel-cycle-fac/ur-deconversion.html>

UNCLASSIFIED

GLE Hitachi and DU Tails

- The US Department of Energy (DOE) has agreed to sell around 300,000 tonnes of depleted uranium hexafluoride to GE Hitachi Global Laser Enrichment (GLE) for re-enrichment at a proposed plant to be built near DOE's Paducah site in Kentucky.*
- Once the plant is complete it is estimated to take 40 years to enrich the stockpile of tails.

** <http://www.world-nuclear-news.org/UF-US-DOE-sells-depleted-uranium-for-laser-enrichment-1111167.html>

UNCLASSIFIED

UF6 Cylinder Types v. Enrichment

Cylinder Model	Nominal Diameter inches	Maximum UF ₆ kgs	Maximum U kgs	Maximum Enrichment % ²³⁵ U	Maximum ²³⁵ U kgs
1S	1.5	0.45	0.30	100	0.30
2S	3.5	2.22	1.50	100	1.50
5A/5B	5	24.95	16.9	100	16.9
8A	8	115.7	78.2	12.5	9.8
12A/12B	12	208.7	141.1	5.0	7.1
30B	30	2,277	1,540	5.0	77
48A/X	48	21,030	14,219	4.5	640
48F	48	27,030	18,276	4.5	822
48G	48	26,840	18,148	1.0	181
48Y	48	27,560	18,634	4.5	839
48H/HX/OM	48	27,030	18,276	1.0	183

George Eccleston & Ed Wonder, NMMSS Users Group Meeting, Las Vegas, NV, May 18, 2010

UNCLASSIFIED

Who Enriches Uranium?

World Enrichment capacity – operational and planned (thousand SWU/yr)

Country	Company and plant	2013	2015	2020
France	Areva, Georges Besse I & II	5500	7000	8200
Germany-Netherlands-UK	Urenco: Gronau, Germanu; Almelo, Netherlands; Capenhurst, UK.	14,200	14,200	15,700
Japan	JNFL, Rokkaasho	75	1050	1500
USA	USEC, Paducah & Piketon	0*	0	3800
USA	Urenco, New Mexico	3500	5700	5700
USA	Areva, Idaho Falls	0	0	3300?
USA	Global Laser Enrichment	0	0	3000?
Russia	Tenex: Angarsk, Novouralsk, Zelenogorsk, Seversk	26,000	30,000	37,000
China	CNNC, Hanzhun & Lanzhou	2200	3000	8000
Other	Various	75	500	1000?
Total SWU/yr approx		51,550	61,450	87,200
Requirements (<i>WNA reference scenario</i>)		49,154	51,425	59,939

<http://www.world-nuclear.org/info/Nuclear-Fuel-Cycle/Conversion-Enrichment-and-Fabrication/Uranium-Enrichment/>

UNCLASSIFIED


Iran's Enrichment Facilities*

- Iran has declared enrichment sites at Natanz and Fordow
- It also conducts conversion operations at Isfahan**

Iran's nuclear facilities



Source: New Scientist/ Global Security



*<http://www.bbc.com/news/world-middle-east-11927720>

**also spelled Esfahan per <https://www.state.gov/documents/organization/245318.pdf>

UNCLASSIFIED

DPRK and Uranium Enrichment*

- 2010: Sig Hecker visits DPRK and is shown new enrichment facility at Yongbyon
 - Told there were 2000 centrifuges
- In February 2012, North Korea announced that it would suspend uranium enrichment at Yongbyon, and not conduct any further tests of nuclear weapons while productive negotiations involving the United States
- Restart of facilities occurred in 2013

*<http://www.bbc.com/news/world-asia-pacific-11813699>

UNCLASSIFIED

Summary

- Conversion and enrichment of uranium is usually required to obtain material with enough ^{235}U to be usable as fuel in a reactor or weapon
- The cost, size, and complexity of practical conversion and enrichment facilities aid in non-proliferation by design
 - Although some approaches lend themselves more easily to proliferation than others

UNCLASSIFIED